

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Premium Flashing Cement
<b>Description</b>	BH5600 is an asbestos free, fiber-reinforced, premium asphalt roof cement suitable for trowel application to roofing and flashing. BH5600 has excellent vertical slump resistance and exhibits a smooth consistency easily applied by the roofing professional.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Excellent vertical slump resistance</li> <li>• Smooth trowel consistency</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Construction of roof flashings</li> <li>• Vertical and horizontal applications</li> </ul>
<b>Color</b>	Black
<b>Solids Content</b>	By volume 71% – 76%
<b>Theoretical Coverage Rate</b>	14 sq ft per gallon at 1/8 in thickness
<b>VOC Value(s)</b>	< 350 g/l (2.92 lbs/gal)
<b>Limitations</b>	Not all APP membranes are alike and adhesion to these modified membranes should be tested. Do not use with membranes containing a burn off film.

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

## MIXING & THINNING

<b>Mixing</b>	No mixing required
<b>Thinning</b>	Do not thin

## APPLICATION EQUIPMENT GUIDELINES

<b>Trowel</b>	Use bull nose roofing trowel.
---------------	-------------------------------

## CLEANUP & SAFETY

<b>Cleanup</b>	Mineral spirits or equivalent solvent.
<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

## Ventilation

Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	12 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
<b>Shipping Weight</b>	43 lbs per 5 gallon pail Net contents 4.7 gallons
<b>Storage Temperature &amp; Humidity</b>	40°F – 110°F (4°C – 43°C) 0 – 100% relative humidity
<b>Storage</b>	Store indoors. This product is not affected by excursions below published storage temperatures. Always inspect the product prior to use to make sure it is smooth and homogeneous.

## PERFORMANCE DATA

Specifications	Category	Results
ASTM 4586	Type 1	Pass

Rev 12/18

### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchase or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).