#### **DESCRIPTION**

PENNTROWEL Epoxy L/F Lining System is a multiple component glass mat reinforced monolithic lining system that offers the benefits of increased strength and chemical resistance by incorporating glass mat reinforcement and a multiple layer build.

PENNTROWEL Epoxy L/F has been formulated to perform in chemical immersion, as well as splash and spill, and heavy traffic environments. The system can perform well in the wide range of temperatures common to sumps, trenches, pits and vessels.

Consult Corrosion Engineering specification CES-352 for complete usage and installation details.

## **FEATURES**

- Excellent physical properties.
- Extremely low absorption and shrinkage.
- Excellent chemical resistance.
- Reinforcing adds strength thus reducing the possibility of cracking.

## **AREAS OF USE**

PENNTROWEL Epoxy L/F is used to protect concrete and steel substrates in trenches, pits, vessels, sumps, manways, and floors - both in and out of doors that are subjected to a wide variety of corrosive agents.

NOTE: Use PENNTROWEL Epoxy L/F System Carbon Grade in hydrofluoric acid or hot caustic chemical service.

### **TYPICAL PHYSICAL PROPERTIES**

| PROPERTY   | SILICA       | CARBON          |
|--|--------------|-----------------|
| Wet Density, lbs/cu. ft.                                   | 110          | 101             |
| Compressive Strength, psi (ASTM C-579)                     | 9,200        | 14,300          |
| Tensile Strength, psi (ASTM C-307)                         | 1,700        | 2,200           |
| Coefficient of Expansion, in./in/°F (ASTM<br>C-531)        | 3.4 x 10⁻⁵   | 3.5 x 10⁻⁵      |
| Shrinkage, (ASTM C-531) @ 28 days                          | 0.13%        | 0.11%           |
| Modulus of Elasticity, psi (ASTM C-580)                    | 8.8 x 10⁵    | 6.2 x 10⁵       |
| Flexural Strength, psi (ASTM C-580)                        | 3,100        | 4,500           |
| Service Temperature Limit (Depending on chemical exposure) | 160°F-180° F | 160°F-<br>180°F |

# **ESTIMATING/PACKAGING THEORETICAL QUANTITIES – NO OVERAGE ALLOWANCE**

| STEP   | PRODUCT   | CODE                    | PACKAGING   | COVERAGE                                |
|--|---|-------------------------|---|---|
| Primer                                       | PENNTROWEL Epoxy Primer   | 19676                   | 4 x 1 gal units/case  | 600 SF/case (150 SF/ gal) @ 11 mils WFT |
| Basecoat for Silica Grade                    | PT Epoxy Resin<br>PT Epoxy Hardener<br>PT L/F Filler  | 19680<br>19677<br>19642 | 4 x 9.2 lb (1 gal) cans/case<br>4 x 0.75 lb (0.75 pt) cans/case<br>2 x 55 lb bags<br>150 lb unit (1.36 cu ft) | 262 SF @ 1/16" per 150 lb unit          |
| Glass cloth (10 oz)                          | L/F Reinforcing Mat   | 19513                   | 38" x 400' (1200 SF) roll   | 1200 SF / roll                          |
| Saturant for cloth                           | PT Epoxy Resin<br>PT Epoxy Hardener   | 19680<br>19677          | 4 x 1 gal (9.2 lb) cans/case<br>4 x 0.75 pt. (0.75 lb) cans/case  | 400 SF/case                             |
| Build Coat                                   | Both the silica and carbon grades utilize a build coat. Use same product codes packaging and coverages as for Base coat information provided above and below. |                         |   |   |
| For PENNTROWEL Epoxy Carbo                   | on Grade, substitute the following  | for Base Coat           | and Cloth layers above  |   |
| Base Coat and Build Coat for<br>Carbon Grade | PT Epoxy Resin<br>PT Epoxy Hardener<br>PT L/F Filler Carbon   | 19680<br>19677<br>29446 | 4 x 1 gal (9.2 lb) cans/case<br>4 x 0.75 pt. (0.75 lb) cans/case<br>2 x 36 lb bags<br>112 Lb unit (1.1 cu ft) | 210 SF @ 1/16" WFT per 112 lb unit      |
| Reinforcing mat for Carbon<br>Grade          | Nexus <sup>®</sup> Veil   | 21925                   | 48" x 500 yd (6000 SF) roll   | 6000 SF/roll                            |

#### Rev 11/2023 - Supersedes 10/2018

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein, and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.

ErgonArmor, a Division of Ergon Asphalt & Emulsions, Inc. | P.O. Box 1639, Jackson, MS 39215-1639 | 601-933-3381 Fax | 601-933-3595 Phone | 877-98ARMOR Toll-Free | ergonarmor.com