

# CE-281 Page 1 of 2 Corlok™ B Mortar

#### **SELECTION & SPECIFICATION DATA**

Туре	Potassium silicate brick mortar	R	
Description	Corlok B Mortar is a 2-component, halogen-free potassium silicate brick mortar used to bond and bed acid brick in chemical environments.	3   1    0	
Uses	<ul> <li>Butter industrial ceramics such as acid brick</li> <li>Brick linings in contact plant sulfuric acid manufacturing process vessels</li> <li>Brick linings in industrial and thermal power plant chimneys</li> </ul>	R	
Features	<ul> <li>Extensive 45+ year history of performance</li> <li>Creamy, buttery consistency</li> <li>High temperature resistance</li> <li>Resists strong oxidizing acids including nitric, chromic and sulfuric</li> <li>Low shrinkage</li> </ul>	N	
	<ul> <li>High bond strength</li> <li>No acid washing required</li> <li>Fluoride-, sodium- and calcium-free, eliminates potential sulfation-hydration reactions</li> </ul>	v	
Limitations	• Not for use beyond its chemical resistance or thermal capabilities. Do not use in hydrofluoric acid service or caustic environments. Consult ErgonArmor with specific questions.		
		<u> </u>	
		7	
		<u>s</u>	
		s	
		v	

## **INSTALLATION GUIDANCE**

Reference Specifications	CES-358 ErgonArmor Specification for Brick Mortar Mixing	
Installation Conditions	Corlok B Mortar is formulated for ideal handling at 70°F (21°C). Do not use if temperature of mortar or components are below 50°F (10°C). If temperatures are below 50°F (10°C), condition components and substrate before application.	
Ratio	1.0 part solution: 2.5 parts powder by weight.	
	Powder loading may be individual bricklayer har	, ,
Mixing	Pour measured quantity of solution into clean, dry mixing vessel. Slowly add measured quantity of powder to solution and mix thoroughly until fully blended.	
Work Life	2-3 hours at 50°F (10°C) 60-80 minutes at 70°F (21°C) 30-40 minutes at 90°F (32°C)	
Cleanup	Water	
CURE TIME		
Temperature	Initial Set	Full Cure
70°F (21°C)	5-6 hours	72-96 hours
<u>SAFETY</u>		
Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.	
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.	



PACKAGING, ESTIMATING & HANDLING

solution and 2 x 55 lb (25 kg) bags of powder.

Code

19554

19553

19539

with storage conditions.

A 1.25 cubic foot (154 lb or 70 kg) unit consists of 1 x 44 lb (20 kg) pail of

Product

Corlok B Solution

Corlok B Powder

Theoretical

Coverage

Storage &

Shelf Life

## CE-281 Page 2 of 2 Corlok ™ B Mortar

### **TYPICAL PHYSICAL PROPERTIES**

Property	Typical Value
Color	White
Density, ASTM C138	123 lb/ft³ (1,970 kg/m³)
Compressive strength, 28-day, ASTM C579	>5,400 psi (37 MPa)
Tensile strength, 7-day, ASTM C307	>350 psi (2.4 MPa)
Flexural strength, ASTM C453	>1,300 psi (9 MPa)
Bond strength to brick (pull blocks)	>180 psi (1.2 MPa)
Maximum service temperature	1,650°F (900°C)

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

Consumption will vary based on brick size and joint width. Consult estimating guide CES-145.

Maintain products in original packaging and

sealed until ready for use. Estimated shelf life for

dry area at 70°F (21°C). Actual shelf life may vary

the solution is 12-18 months when stored in a

Packaging

44 lb (20 kg) pail

55 lb (25 kg) bag

600 lb (272 kg) drum

#### Rev 08/2021

#### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.

Division of Ergon Asphalt & Emulsions, Inc. | P.O. Box 1639, Jackson, MS 39215-1639 | 601-933-3381 Fax | 601-933-3595 Phone | 877-98ARMOR Toll-Free | ergonarmor.com