

## Blackhawk™ 5164 Asphalt Primer

## SELECTION & SPECIFICATION DATA

**Asphalt Cutback Primer Type** 

Blackhawk 5164 Asphalt Primer is a quick-drying, Description

highly penetrating primer to be used in conjunction with modified bituminous roofing materials. It dries consistently under varying weather conditions, and employs a quick dry proprietary solvent that yields a

firm residue once cured.

Primer for roofing substrates using hot, cold and torch Uses

applied asphalt roof membranes.

Color Black

<350 g/L (2.92 lbs/gal) VOC Value(s)

SUBSTRATES & SURFACE PREPARATION

All surfaces must be clean and free from debris and Concrete loose scale material or anything that may interfere

with adhesion or act as a bond breaker with the

desired substrate.

MIXING & THINNING

No mixing necessary. Mixing

**Thinning** Do not thin

Mineral spirits or equivalent solvent. Cleanup

APPLICATION GUIDELINES

Spray **Application**  Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve

the desired results.

**Airless Spray** Single Leg

Pump Size: 15:1 or greater Hose diameter: 3/8-inch Tip size: 0.019 - 0.021-inch

Apply with a wide fiber brush in order to create a **Brush** 

smooth uniform film.

Roller Use a low nap phenolic core roller. PACKAGING, HANDLING & STORAGE

**PACKAGING** ITEM#

Pail - 4.7 gallons K-5164-005-001-UN

Drum - 53 gallons K-5164-053-001-UN

**Theoretical Coverage Rate**  0.35 - 0.6 gal/100 square feet

Storage &

**Shelf Life** 

Store indoors. This product is not affected by excursions below published storage temperatures. Always inspect the product prior to use to make sure

it is smooth and homogeneous.

**SAFETY** 

Mixes and applications of this product present a Safety

number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets

before using.

Thorough air circulation must be used during and Ventilation

after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS

for further information.

PERFORMANCE DATA

**SPECIFICATIONS CATEGORY** RESULTS

ASTM D41 Pass

Rev. 12/2025

## TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see armor-inc.com.