

Epoxy Cold Room Hardener

SELECTION & SPECIFICATION DATA

| | |
|--------------------|--|
| Type | Cold temperature epoxy hardener |
| Description | Epoxy Cold Room Hardener is a modified amine curative designed for use with Penncoat™, Penntrowel™, Thinset™, and Tufchem™ epoxy resins at application temperatures between 35°F (2°C) and 50°F (10°C). |
| Uses | <p>Cold temperature hardener for the following epoxy resins:</p> <ul style="list-style-type: none"> • Penncoat 221 Resin • Penncoat 227 Resin • Penntrowel 250 Resin • Penntrowel Epoxy Resin • Penntrowel Epoxy Primer Resin • 6710 Resin • Thinset Resin • Tufchem Epoxy Resin |
| Features | <ul style="list-style-type: none"> • Easy-to-measure mix ratios • Expands use of compatible resins to 35°F (2°C) to 50°F (10°C) application temperatures • Meets or exceeds chemical resistance performance of replaced, standard hardener |
| Limitations | <ul style="list-style-type: none"> • All resins, including Penntrowel Epoxy Primer Resin and Penntrowel 250 Resin, hardened with this curative are not moisture/damp surface tolerant during application or cure. • Uncured products using this hardener are not 100% solids and contain VOC's. |

INSTALLATION GUIDANCE

| | | | |
|---------------------------------|--|----------------------------|----------------------------|
| Reference Specifications | Refer to product data sheet and installation specification for specific system. | | |
| Installation Conditions | Epoxy Cold Room Hardener is formulated for use at temperatures between 35°F (2°C) and 50°F (10°C). Substrate must be dry during application. | | |
| Mix Ratio | Part A Resin | Mix ratio by volume | Mix ratio by weight |
| | Penncoat 221 Resin | 8: 1 | 1: 0.10 |
| | Penncoat 227 Resin | 6: 1 | 1: 0.13 |
| | Penntrowel 250 Resin | 5: 1 | 1: 0.16 |
| | Penntrowel Epoxy Resin | 5: 1 | 1: 0.16 |
| | Penntrowel Epoxy Primer Resin | 5: 1 | 1: 0.16 |
| | 6710 Resin | 5: 1 | 1: 0.16 |
| | Thinset Resin | 5: 1 | 1: 0.16 |
| | Tufchem Epoxy Resin | 5: 1 | 1: 0.16 |

Mixing Add hardener to resin and mix thoroughly until fully dispersed and uniform.

Cleanup Mineral spirits

CURE TIME

Generally, when the resin is mixed with Epoxy Cold Room Hardener, the work life and set time at 50°F (10°C) will be close to the work life and set time at 70°F (21°C) had it been mixed with the replaced, standard hardener. Consult ErgonArmor for guidance.

SAFETY

Safety Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

Epoxy Cold Room Hardener

PACKAGING & ESTIMATING

| Product | Code | Packaging |
|---------------------------------|---|---|
| Epoxy Cold Room Hardener | 29447 | 2.5-gal (9.5 L) 20 lb (9.1 kg) jerrycan |
| Theoretical Coverage | <p>Consult the product data sheet for the specific system for theoretical coverage information.</p> <p>Most resins require less volume of Epoxy Cold Room Hardener than standard hardener; therefore, coverage per pail of resin will be reduced when mixed with Epoxy Cold Room Hardener. For 3-component systems using Epoxy Cold Room Hardener, weight of filler required per pail of resin will also be reduced. Consult ErgonArmor for guidance.</p> | |
| Storage & Shelf Life | <p>Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.</p> <p>If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.</p> | |

Rev 01/2021

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.