

# Thinset Novolac Adhesive - Silica

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Novolac epoxy tile adhesive
<b>Description</b>	Thinset Novolac Adhesive - Silica is a 100% solids, 3-component silica-filled novolac epoxy tile and floor paver adhesive.
<b>Uses</b>	<p>High strength bonding adhesive for tile, ceramic, brick, pavers, masonry and steel plates in food, beverage, pharmaceutical and chemical process areas subject to:</p> <ul style="list-style-type: none"> <li>• Severe impact</li> <li>• Thermal shock</li> <li>• Strong sulfuric acid</li> <li>• Strong caustic soda</li> </ul>
<b>Features</b>	<ul style="list-style-type: none"> <li>• Exceptional adhesive bond strength</li> <li>• Superior resistance to strong acids, alkalis and solvents</li> <li>• Enhances thermal shock resistance of bonded tile and pavers</li> <li>• Low odor</li> <li>• Excellent handling</li> <li>• Damp surface tolerant</li> </ul>
<b>Limitations</b>	<ul style="list-style-type: none"> <li>• Not suitable for vertical wall tile applications. Consult with Armor for wall tile applications.</li> <li>• Not for use beyond its chemical resistance or thermal capabilities. Consult Armor with specific questions.</li> </ul>

## INSTALLATION GUIDANCE

<b>Reference Specifications</b>	<p>CES-302 Installation of chemical resistant brick flooring using the bricklayer's method of construction and direct bond technique</p> <p>CES-309 Installation of corrosion-resistant tile/brick using the tile setter's method of construction</p> <p>CES-311 Installation of Tufchem Tiling Systems</p>
<b>Installation Conditions</b>	Thinset Novolac Adhesive - Silica is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. For installation temperatures between 35°F (2°C) and 50°F (10°C), substitute Epoxy Cold Room Hardener for 6711 Hardener. Bricks or tiles must be clean, dry and neutral pH.
<b>Ratio</b>	<p>For installation temperatures between 50°F (10°C) and 90°F (32°C), use 6711 Hardener at the following mix ratios:</p> <p>1.0 resin: 0.51 hardener: 3.1 filler by weight 5 resin: 3 hardener by volume (liquids only)</p> <p>For installation temperatures between 35°F (2°C) and 50°F (10°C), use Epoxy Cold Room Hardener at the following mix ratios:</p> <p>1.0 resin: 0.16 hardener: 2.4 filler by weight 5 resin: 1 hardener by volume (liquids only)</p>
<b>Mixing</b>	Pour measured quantity of resin into clean, dry mixing vessel. Slowly add measured quantity of hardener to resin and mix thoroughly. After liquids are mixed completely, add filler and mix until filler is thoroughly wetted and adhesive is creamy, free of lumps and trowelable.
<b>Work Life</b>	<p>30-40 minutes at 70°F (21°C).</p> <p>Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.</p>
<b>Cleanup</b>	Xylene or methyl ethyl ketone (MEK)

## CURE TIME

Brick or Tile Temperature	Initial Set	Heavy Traffic	Full Cure
70°F (21°C)	4-6 hours	36 hours	7 days

# Thinset Novolac Adhesive - Silica

## PACKAGING & ESTIMATING

Product	Code	Packaging
6710 Resin Gray	19591	4 x 7.8 lb (0.8 gal) can case
6711 Hardener	19593	4 x 4.0 lb (0.5 gal) can case
Thinset Filler	19697	48 lb (21.8 kg) bag
Epoxy Cold Room Hardener	29447	2.5-gal (9.5 L) 20 lb (9.1 kg) jerrycan

A 143 lb (1.3 ft<sup>3</sup>) unit consists of 1 case of resin, 1 case of 6711 Hardener, and 2 x 48 lb bags of filler.

When using Epoxy Cold Room Hardener, 111 lb (1 ft<sup>3</sup>) of mixed material consists of 1 case of resin, 5 lb of Epoxy Cold Room Hardener and 75 lb of filler.

**Theoretical Coverage** A 143 lb unit will cover 125 sf (11.6 m<sup>2</sup>) at 1/8-inch (3.2 mm) or 150 sf (13.9 m<sup>2</sup>) at 3/32-inch (2.4 mm) thickness.

111 lb of Thinset Novolac Adhesive - Silica with Epoxy Cold Room Hardener will cover 96 sf (8.9 m<sup>2</sup>) at 1/8-inch (3.2 mm) or 120 sf (11 m<sup>2</sup>) at 3/32-inch (2.4 mm) thickness.

Allow for loss in mixing and use.

**Storage & Shelf Life** Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with Armor.

## SAFETY

**Safety** Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

**Ventilation** Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

## TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	Gray
Density, ASTM C138	110 lb/ft <sup>3</sup> (1,629 kg/m <sup>3</sup> )
Compressive strength, ASTM C306 24-hour 28-day	>6,000 psi (41.4 MPa) >12,000 psi (82.8 MPa)
Tensile strength, 7-day, ASTM C307	>2,500 psi (17.2 MPa)
Flexural strength, 7-day, ASTM C453	>4,500 psi (31 MPa)
Bond to fully vitrified tile	>2,000 psi (13.8 MPa)
Adhesion to concrete	> strength of concrete
Water absorption, ASTM C413	<0.15%
Service temperature at bond line under tile	190°F (88°C)

Rev 06/2026

## TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see armor-inc.com.