



### SELECTION & SPECIFICATION DATA

Type	Polyamide Epoxy
Description	Novocoat SP2000AR Ceramic Coating is a highly abrasion resistant coating that forms a strong bond, even to damp and marginally prepared surfaces including tightly adhered rust. Suitable for use on concrete, steel, or surface rebuilding and restoration products, this low-friction overcoat resists build-up and offers long-term wear protection.
Features	<ul style="list-style-type: none"><li>• 100% solids, no VOCs</li><li>• Excellent immersion resistance</li><li>• Long-term wear protection</li><li>• Excellent abrasion resistance</li><li>• Meets AWWA 210 performance requirements</li></ul>
Uses	<ul style="list-style-type: none"><li>• Chutes</li><li>• Hoppers</li><li>• Silos</li></ul>
Color	Light gray
Finish	Gloss
Dry Film Thickness (DFT)	8 – 10 mils per coat
Solids Content	99 – 100% by volume

### SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants.
Steel	<p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 – 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 3 Commercial Blast with angular profile of 1.5 – 3.0 mils, SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>
Concrete or Concrete Masonry Unit (CMU)	Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with SSPC-SP 13/NACE 6. Required surface profile is CSP 3-5. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days. Prime with Novocoat SC1100 Concrete Primer.
Previously Painted Surfaces	Consult with ErgonArmor Technical Service.

### MIXING & THINNING

Ratio	3A:1B by volume for plural spray
Mixing	For single leg spray, brush, or roller, do not mix partial kits. Power mix parts A and B separately then combine and power mix.
Thinning	Spray: Up to 6.5 oz/gal (5%) with Novocoat TH1710 Thinner Brush: Up to 16 oz/gal (12%) with Novocoat TH1710 Thinner Roller: Up to 16 oz/gal (12%) with Novocoat TH1710 Thinner
Pot Life	8 hours 20 minutes at 41°F (5°C) 2 hours at 77°F (25°C) 35 minutes at 90°F (32°C)  Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.
Cleanup	MEK or Acetone

### APPLICATION GUIDANCE

Spray Application	The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.
Airless Spray Plural Component	Tip Size: 0.025 – 0.029 reversible type Part A Fluid Line: 1/2 in ID Part B Fluid Line: 3/8 in ID Spray Line: 1/2 in ID x 50 feet maximum Whip: 1/4 in – 3/8 in ID Whip Length: 10 feet maximum Pump Size: 56:1 or greater Output Pressure: 4,500 – 6,000 psi, filter removed Static Mixer: 2 x 1/2 in ID x 12 in (24 inches total length) behind mixing valve Part A Temperature: 130°F – 135°F (54°C – 57°C) Part B Temperature: 90°F – 95°F (32°C – 35°C)
Airless Spray Single Leg or Hot Pot	Pump Size: 65:1 or greater Output: 4,000 – 6,000 psi, filter removed Hose Length: 50 ft x 3/8 in Whip Length: 10 ft x 1/4 in  Part A resin and Part B hardener should be heated individually to 75°F – 85°F (24°C – 29°C) before mixing so product will atomize properly in delivering paint to the substrate.
Brush & Roller	This material may be applied with brush or roller. Be aware of work life when using brush or roller application.
Brush	Medium bristle brush.
Roller	Short-nap synthetic roller cover with phenolic core.



### CURE SCHEDULE & RECOAT WINDOW

TEMPERATURE	MINIMUM RECOAT	MAXIMUM RECOAT	RETURN TO SERVICE (HYDROCARBON IMMERSION)
50°F (10°C)	8 hours	14 days	7 days
77°F (25°C)	4 hours	14 days	72 hours
140°F (60°C)	1 hour	Not Recommended	4 hours

Return-to-service varies with chemical exposure. Consult ErgonArmor Technical Service for guidance.

### SAFETY

#### Safety

Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

#### Ventilation

Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

### ESTIMATING & PACKAGING

#### Theoretical Coverage

200 square feet per gallon at 8 mils  
160 square feet per gallon at 10 mils  
Allow for loss in mixing and application.

#### Package Sizes

Light Gray, 4 x 2.6 lbs (1.2 kg) Kit Case  
Each 2.6 lbs (1.2 kg) Kit includes  
- Part A Resin Light Gray, 2.2 lb (1 kg) Jar  
- Part B Hardener, 0.4 lb (0.2 kg) Jar  
- Mixing knife and chip brush  
Item #: M-SP1510-QTCS-01

Light Gray, 1 gal (3.7 L) Kit  
- Part A Resin Light Gray 0.73 gal (2.7 L) Pail  
- Part B Hardener, 0.26 gal (1 L) Bottle  
Item #: M-SP1510-1GLKT-01

Light Gray, 4 gal (15.2 L) Kit  
- Part A Resin Light Gray, 2.9 gal (11 L) Pail  
- Part B Hardener, 1.1 gal (4.2 L) Pail  
Item #: M-SP1510-4GLKT-01

#### Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

### TYPICAL PHYSICAL PROPERTIES

TEST METHOD	SYSTEM	RESULTS
Dry adhesion ASTM D4541	Blasted steel 1 coat	>2,500 psi
Wet adhesion ASTM D4541 5 days 158°F (70°C) water	Blasted steel 1 coat	>2,500 psi
Abrasion ASTM D4060 1000 cycles, CS17 wheel 1000 gm load	Blasted steel 1 coat	24 mg loss
Compressive strength ASTM C109	Blasted steel 1 coat	10,000 – 13,000 psi
Hardness ASTM D2240	Blasted steel 1 coat	83 – 90 Shore
Meets the performance requirements of AWWA C210		

### TEMPERATURE RESISTANCE

SERVICE	MAXIMUM TEMPERATURE
Dry, continuous	220°F (104°C)
Dry, non-continuous	250°F (121°C)
Under insulation	175°F (79°C)

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

Discoloration and loss of gloss occur above 200°F (93°C) but do not affect performance.

Rev 02/2021

#### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).