

SELECTION & SPECIFICATION DATA

Type	Epoxy Paste/Caulk
Description	Novocoat SP2900 Paste is a two-component 100% solids trowel-grade epoxy novolac metal repair paste commonly used to repair tank chimes, fill pitted surfaces and feather lap welds before top-coating with Novocoat SC3300 Novolac Lining or Novocoat SP2000 Series coatings. Excellent resistance to a wide range of petrochemicals, fuels, organic/inorganic acids and alkalis. Long recoat window allows it to be top-coated up to 14 days, depending on temperatures.
Features	<ul style="list-style-type: none"> • 100% solids, no VOCs • Application and cure at room temperature • Multipurpose durable repair composite • No shrinkage, expansion or distortion • Quick return-to-service • Fully machinable using conventional tools
Uses	<ul style="list-style-type: none"> • Anchor adhesive • Resurface of pitted metal surfaces • Leak repair • Plate bonding • Pump casing • High strength structural adhesive for metal bonding
Color	Light gray
Finish	Matte
Primer	Self-priming
Solids Content	100% by volume

SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants.
Steel	<p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 – 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 2 Commercial Blast with angular profile of 1.5 – 3.0 mils, SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool Cleaning are suitable for mild environments.</p>
Weld Repair	Use a flame to sweat out oil from deeply impregnated surfaces. Stabilize cracks by drilling the extremities. Long cracks should be drilled, tapped and bolted every few inches. Vee-out all cracks using a file. Degrease using clean rags.
Substrate Temperature	Surface should be at least 50°F (10°C) and relative humidity not to exceed 90%. Maximum substrate temperature should be kept to 140°F (60°C). Contact ErgonArmor for conditions where the substrate temperature exceeds 140°F (60°C).

MIXING & THINNING

Mixing	Do not mix partial kits. To mix small kits, transfer the entire contents of resin and hardener onto the plastic mix board. Mix thoroughly together until color of material is uniform and free of any streaks. To mix large kits, combine resin and hardener and mix with a mechanical mixer.
Thinning	Do not thin.
Pot Life	45 minutes in 8 fl oz mass at 77°F (25°C)
	Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.
Cleanup	MEK or Acetone

APPLICATION GUIDANCE

Application	Apply directly onto the prepared surface with the plastic applicator or spatula provided. Press down firmly to remove entrapped air, fill all cracks, and ensure maximum contact with the surface. Use reinforcement cloth over holes and cracks. Fully machinable using conventional tools once cured.
Brush & Roller	Brush or roller can be used to smooth uncured surface with solvent if desired.

CURE SCHEDULE & RECOAT WINDOW

TEMPERATURE	MINIMUM RECOAT	MAXIMUM RECOAT	RETURN-TO-SERVICE (HYDROCARBON IMMERSION)
50°F (10°C)	12 hours	14 days	7 days
77°F (25°C)	3 hours	14 days	24 hours
140°F (60°C)	1 hour	7 days	4 hours

Return-to-service will vary with chemical exposure. Consult with ErgonArmor Technical Service for guidance.

Tack free at 77°F (25°C) ASTM D1640	3.5 hours for 25 – 30 mil DFT
Dry hard at 77°F (25°C) ASTM D1640	8 hours for 25 – 30 mil DFT

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

ESTIMATING & PACKAGING

Theoretical Coverage	12.8 square feet per gallon at 125 mils Allow for loss in mixing and application.
Package Sizes	<p>Light Gray, 4 x 2.1 lbs (0.95 kg) Kit Case Each 2.1 lbs (0.95 kg) Kit includes</p> <ul style="list-style-type: none"> - Part A Resin Light Gray, 1.8 lbs (0.8 kg) Jar - Part B Hardener, 5.6 oz (159 g) Jar - Mixing knife, spreader <p>Each case includes</p> <ul style="list-style-type: none"> - Mixing board <p>Item #: M-SP2910-QTCS-01</p> <p>Light Gray, 10.6 lbs (4.8 kg) Kit</p> <ul style="list-style-type: none"> - Part A Resin Light Gray, 8.8 lbs (4.0 kg) Pail - Part B Hardener, 1.8 lbs (0.8 kg) Jar <p>Item #: M-SP2910-1GLKT-01</p>
Storage & Shelf Life	<p>Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 24 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.</p> <p>If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.</p>

TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE
Dry adhesion ASTM D4541 Blasted steel 1 coat	>2,850 psi
Flash point	Greater than 250°F (121°C)
Specific gravity	Part A: 1.36 Part B: 0.82
VOC	0 grams/liter
Density	Part A: 11.29 lbs/gal Part B: 6.81 lbs/gal

SERVICE TEMPERATURE

SERVICE	TEMPERATURE
Dry	250°F (121°C)
Splash/spill	200°F (93°C)
Immersion	150°F (65°C)

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

Rev 02/2021

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.