

SELECTION & SPECIFICATION DATA

Type	Vinyl ester brick mortar
Description	PC1000 Mortar is a 2-component vinyl ester brick mortar. PENNCHEM Mortar Initiator may be added to speed cure at cool temperatures.
Uses	PC1000 Mortar is used to butter chemical resistant ceramics such as acid brick and tile, including structural glazed tile used in pulp and paper processing facilities.
Features	• Easy workability • Non-slumping consistency • Rapid strength gain • Resistant to oxidizing chemicals • Resistant to bleaches such as chlorine and chlorine dioxide
Limitations	• Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.

INSTALLATION GUIDANCE

Reference Specifications	CES-358	ErgonArmor Specification for Brick Mortar Mixing
Installation Conditions	PC1000 Mortar is formulated for ideal handling at 70°F (21°C). For temperatures between 35°F (2°C) and 50°F (10°C), add PENNCHEM Mortar Initiator to accelerate cure.	
Ratio	1.0 part resin: 3.5 - 4.0 parts powder by weight Ratio may be adjusted slightly to suit individual brick layer or tile setter handling preferences. 1.75 fl. oz. initiator: 40 lb. resin, as conditions require	
Mixing	Pour measured quantity of resin into clean, dry mixing vessel. Slowly add measured quantity of powder to resin and mix until thoroughly wetted. When adding Pennchem Mortar Initiator, pour measured amount of Initiator directly into the pail of resin and stir thoroughly before combining with powder as described above.	
Work Life	PC1000 Mortar without Initiator: 40 - 60 minutes at 50°F (10°C) 30 - 40 minutes at 70°F (21°C) 10 - 20 minutes at 90°F (32°C) Consult ErgonArmor for information on the effect of PENNCHEM Mortar Initiator on set time. A larger volume of mixed material will have a shorter work life than a smaller volume.	
Cleanup	MEK	

CURE TIME

Temperature	Initial Set	Full Cure
70°F (21°C)	40 - 60 minutes	36 hours

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

PACKAGING & ESTIMATING

Product	Code	Packaging
PC1000 Resin	24346	40 lb (18.1 kg) pail
PENNCHEM Powder	19685	50 lb (22.6 kg) bag
PENNCHEM Mortar Initiator	19524	32 fl. oz. bottle

A 190 lb unit consists of 1 x 40 lb pail of resin and 3 x 50 lb bags of powder. Dosage rate for PENNCHEM Mortar Initiator when added to resin is 1.75 fl. oz of initiator per pail of resin.

Theoretical Coverage

Consumption will vary based on ceramic or masonry unit size and joint width.

Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life of resin and powder is 6 months when stored in a dry area at 70°F (21°C). Store resin between 55°F (13°C) and 65°F (18°C) for maximum shelf life. Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	White
Density, ASTM C138	118 lb/ft ³ (1,890 kg/m ³)
Compressive strength, ASTM C579	>10,000 psi (69 MPa)
Tensile strength, ASTM C190	>1,500 psi (10.3 MPa)
Absorption, ASTM C413	0.2%
Bond strength to brick, pull blocks	>275 psi (1.9 MPa)
Maximum service temperature	210°F (99°C)

Rev 09/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.