

Blackhawk™ 5404 Rubberized Flashing Cement

SELECTION & SPECIFICATION DATA

Type Rubberized Flashing Cement

Description Blackhawk 5404 Rubberized Flashing Cement is a premium,

trowel grade, rubberized bitumen mastic. Blackhawk 5404 cures to a durable waterproof membrane capable of accommodating minor expansion and contraction.

Uses • Night seals

Three coursing
Setting roof drains

• Adhering bituminous laps and flashing

· Vertical and horizontal application

Color Black

Primer Self-priming

Topcoats Once cured, product can be topcoated with urethane,

acrylic or silicone. Blackhawk 5404 can also receive granule

embedment while still wet.

Dry Film

Thickness (DFT)

1/8-inch is typical

VOC Value(s) <250 g/l (2.09 lbs/gal)

SUBSTRATES & SURFACE PREPARATION

All surfaces must be clean and free from debris and loose

scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.

MIXING & THINNING

Mixing No mixing required

Thinning Do not thin

Cleanup Mineral spirits or equivalent solvent

APPLICATION GUIDANCE

Trowel 1/8-inch square notched trowel or round/ bullnose roofing

trowel.

PACKAGING, ESTIMATING & HANDLING

 ITEM#
 PACKAGING

 K-5404-003-001
 Pail - 2.7 gallons

 K-5404-005-001
 Pail - 4.7 gallons

Theoretical 14 square feet per gallon at 1/8-inch thickness.

Coverage Rate

Storage & Store indoors. This product is not affected by excursions below published storage temperatures. Always inspect the

product prior to use to make sure it is smooth and

homogeneous.

SAFETY

Safety Mixes and applications of this product present a number of

hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

TYPICAL PHYSICAL PROPERTIES

| SPECIFICATIONS | CATEGORY | RESULTS |
|----------------------|--------------------------|---------|
| ASTM 4586 | Type 1 | Pass |
| ASTM 6511 | Uniformity | Pass |
| ASTM 6511 | Workability | Pass |
| ASTM 6511 Blistering | Behavior at 140°F (60°C) | None |
| ASTM 6511 Cracking | Pliability at 32°F (0°C) | Pass |
| Sag/Slide | Behavior at 140°F (60°C) | Pass |

Rev. 12/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see armor-inc.com.