

SELECTION & SPECIFICATION DATA

Type	Structural epoxy grout																				
Description	Tufchem XF Grout is a versatile structural epoxy grout designed with low shrinkage, low exotherm, and high flow for grouting and casting applications. It may be placed 3/4 inches (20 mm) to 12 inches (300 mm) deep per lift.																				
Uses	- Restoring and protecting Portland cement concrete structures such as: <table> <tr> <td>Beams</td><td>Columns</td></tr> <tr> <td>Bases</td><td>Pads</td></tr> <tr> <td>Floors</td><td>Piers</td></tr> <tr> <td>Foundations</td><td>Piles</td></tr> <tr> <td>Footings</td><td>Pedestals</td></tr> </table> - Grouting base plates of rotating and reciprocating machinery such as: <table> <tr> <td>Ball mills</td><td>Pumps</td></tr> <tr> <td>Blowers</td><td>Mixers</td></tr> <tr> <td>Centrifuges</td><td>Generators</td></tr> <tr> <td>Crushers</td><td>Stamping machines</td></tr> <tr> <td>Compressors</td><td>Paper mill machines</td></tr> </table>	Beams	Columns	Bases	Pads	Floors	Piers	Foundations	Piles	Footings	Pedestals	Ball mills	Pumps	Blowers	Mixers	Centrifuges	Generators	Crushers	Stamping machines	Compressors	Paper mill machines
Beams	Columns																				
Bases	Pads																				
Floors	Piers																				
Foundations	Piles																				
Footings	Pedestals																				
Ball mills	Pumps																				
Blowers	Mixers																				
Centrifuges	Generators																				
Crushers	Stamping machines																				
Compressors	Paper mill machines																				
Features	- EZ Mix resin packaging enables efficient resin and hardener mixing for a 2.2 ft³ (0.06 m³) mix. - Low exotherm allows deep pours up to 12 inches (300 mm) without overheating. - Excellent flow characteristics with full filler loading. - Low dust generation during mixing. - Excellent vibration resistance. - Good resistance to a broad range of chemicals and oils. - High physical strength. - Good bond to concrete and metal surfaces. - Rapid strength gain.																				
Limitations	Requires use of formwork for vertical applications.																				

INSTALLATION GUIDANCE

Reference Specifications	CES-360 Installation of ErgonArmor Resinous Polymer Concretes
Installation Conditions	Tufchem XF Grout is formulated for ideal handling at 70°F (21°C). For temperatures below 50°F (10°C), consult ErgonArmor. Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. Substrate must be clean, dry and neutral pH.
Ratio	By weight, 1.0 resin: 0.17 hardener: 7.7 filler or 1.0 part mixed resin and hardener: 6.6 parts filler
Mixing	For the 2.2 ft ³ (0.06 m ³) EZ Mix unit, the part B hardener can be added directly to the part A resin pail. For larger and smaller units, transfer the resin into a mixing container. While power mixing the resin, slowly empty the hardener into the resin then continue mixing for 2 minutes. Transfer the catalyzed resin into a clean, dry paddle mixer then slowly add filler while mixing. Continue mixing until filler is thoroughly wetted.
Work Life	2 hours at 70°F (21°C) Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.
Cleanup	Xylene or MEK

CURE TIME

Temperature	Initial Set	Full Cure
70°F (21°C)	8 hours	5 days

PACKAGING, ESTIMATING & HANDLING

Product	Code	Packaging
Tufchem Epoxy Resin Gray	21928 29436 19704	4 x 7.8 lb (3.5 kg) can case 32.5 lb (14.7 kg) EZ Mix pail 47.0 lb (21.3 kg) pail
Tufchem Epoxy Resin Blue	29437 29657	32.5 lb (14.7 kg) EZ Mix pail 47.0 lb (21.3 kg) pail
Tufchem Epoxy Resin Red	23861 29441 29656	4 x 7.8 lb (3.5 kg) can case 32.5 lb (14.7 kg) EZ Mix pail 47.0 lb (21.3 kg) pail
Tufchem Epoxy Hardener	21929 29438 19705 29554	4 x 1.3 lb (0.59 kg) can case 5.5 lb (2.5 kg) EZ Mix can 7.8 lb (3.5 kg) can 23.4 lb (10.6 kg) can
XF Grout Filler	19600	50 lb (22.7 kg) bag
A 2.2 cubic foot (288 lb) EZ Mix unit consists of 1 x 32.5 lb EZ Mix pail resin, 1 x 5.5 lb EZ Mix can hardener and 5 x 50-lb bags filler.		
A 2.09 cubic foot (276 lb) unit consists of 1 case of 4 x 7.8 lb cans resin, 1 case of 4 x 1.3 lb cans hardener and 240 lbs filler.		
A 3.14 cubic foot (415 lb) unit consists of 1 x 47.0 lb pail resin, 1 x 7.8 lb can hardener, and 360 lbs filler.		
Theoretical Coverage	Allow 132 mixed lb/ft ³ (2,114 kg/m ³) of volume. Allow 16.5 mixed lb/ft ² (80 kg/m ²) when casting as a 1.5-inch (38 mm) overlay and 11.0 mixed lb/ft ² (54 kg/m ²) as a 1.0-inch (25 mm) overlay.	
Storage & Shelf Life	Maintain products in original packaging and sealed until ready for use. Estimated shelf life for the resin and hardener is 12 months when stored in a dry area at 70°F (21°C). Fillers do not degrade with age when stored in a dry area and packaging is intact. Actual shelf life may vary with storage conditions. If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance, consult with ErgonArmor.	

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Density, ASTM C138	132 lb/ft ³ (2,114 kg/m ³)
Compressive strength, ASTM C579	
18 Hours	6,300 psi (44 MPa)
24 Hours	8,250 psi (57 MPa)
30 Hours	10,400 psi (72 MPa)
48 Hours	12,600 psi (87 MPa)
5 Days	>15,500 psi (107 MPa)
Creep, ASTM C1181, 14 Days 3.4MPa (493 psi) 73° F (23° C)	2.0 x 10 ⁻³
Tensile strength, ASTM C307	>2,400 psi (10.3 MPa)
Flexural Strength, ASTM 580	>4,000 psi (27.6 Mpa)
Bond to Concrete ASTM C882 (Slant Shear Strength)	2,415 psi (16.6MPa) Concrete Failure
Flow time, ASTM C1339	
Back of box	<2 minutes
Full contact	<3 minutes
Bearing area, ASTM C1339	Passes
Shrinkage, ASTM C531	0.11%
Absorption, ASTM C413	0.33%
Coefficient of thermal expansion, 75°F- 210°F ASTM C531	19.5 x 10 ⁻⁶ /°F (39.6 x 10 ⁻⁶ /°C)
Minimum application thickness	0.75 inches (20 mm)

Rev. 09/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.