

SELECTION & SPECIFICATION DATA

| | |
|-----------------------|---|
| Type | Epoxy Paste/Caulk |
| Description | Novocoat EP3300 Paste/Caulk SG is a two-component 100% solids trowel applied epoxy novolac caulk formulated for use in warm conditions. This summer grade formula provides longer pot life in higher temperatures. It is commonly used to repair tank chimes or feather lap welds prior to applying Novocoat chemical resistant topcoats. It has excellent resistance to a wide range of petrochemicals, fuels, organic and inorganic acids, and alkalis. |
| Features | <ul style="list-style-type: none"> • 100% solids, no VOCs • Longer pot life in warm conditions • Multipurpose, durable repair composite • No shrinkage, expansion, or distortion • Quick return-to-service under suitable conditions • Fully machinable using conventional tools |
| Uses | <ul style="list-style-type: none"> • Fill pitted metal surfaces • Repair leaks • Rebuild pumps • Bond metal parts |
| Color | Light Gray |
| Finish | Matte |
| Solids Content | 100% solids by volume |

SUBSTRATES & SURFACE PREPARATION

| | |
|--------------------|---|
| All | Substrate must be clean, dry and free of contaminants. |
| Steel | <p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 - 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 3 Commercial Blast with angular profile of 1.5 - 3.0 mils, SSPC-SP 2 Hand Tool or SSPC-SP 3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p> |
| Weld Repair | Use a flame to sweat out oil from deeply impregnated surfaces. Stabilize cracks by drilling the extremities. Long cracks should be drilled, tapped, and bolted every few inches. Vee-out all cracks using a file. Degrease using clean rags. |

MIXING & THINNING

| | |
|-----------------|---|
| Ratio | 1A:1B by volume |
| Mixing | Mix equal parts of the resin and hardener thoroughly until color of material is uniform and free of streaks. |
| Thinning | Do not thin. |
| Pot Life | 25 minutes in a 150g mass at 86°F (30°C) 16 minutes in a 150g mass 122°F (50°C) |
| | Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume. |
| Cleanup | MEK or Acetone |

APPLICATION GUIDELINES

| | |
|---------------------------|--|
| Conditions | Substrate surface temperature 70°F - 140°F (21°C - 60°C) and at least 5°F (3°C) above the dew point and rising. If surface temperature is above 140°F (60°C), consult ErgonArmor Technical Service for guidance. |
| Application | Apply directly onto the prepared surface with the spreader or mixing knife provided. Press down firmly to remove entrapped air, fill all cracks, and ensure maximum contact with the surface. Use reinforcement cloth over holes and cracks. |
| Brush & Roller | Brush or roller can be used to smooth uncured surface with solvent if desired. |

CURE SCHEDULE & RECOAT WINDOW

| TEMPERATURE | MINIMUM RECOAT | MAXIMUM RECOAT | RETURN-TO-SERVICE (HYDROCARBON IMMERSION) |
|--------------|----------------|----------------|---|
| 86°F (30°C) | 1 hour | 48 hours | 7 days |
| 104°F (40°C) | 1 hour | 24 hours | 48 hours |
| 122°F (50°C) | 30 minutes | 8 hours | 24 hours |

Return-to-service will vary with chemical exposure. Consult with ErgonArmor Technical Service for guidance.

| | |
|---|----------------------------------|
| Tack free at 86°F (30°C) ASTM D1640 | 65 minutes for 125 mil DFT film |
| Tack free at 122°F (50°C) ASTM D1640 | 23 minutes for 125 mil DFT film |
| Dry hard at 86°F (30°C) ASTM D1640 | 180 minutes for 125 mil DFT film |
| Dry hard at 122°F (50°C) ASTM D1640 | 30 minutes for 125 mil DFT film |

PACKAGING, ESTIMATING & HANDLING

| ITEM# | PRODUCT | PACKAGING |
|--------------------|--|------------------------|
| M-EP3310S-2GLKT-01 | Novocoat EP3300 SG Paste/Caulk Kit, Light Gray | 24 lb (10.88 kg) Kit |
| | - Part A Resin, White | 12.4 lb (5.62 kg) Pail |
| | - Part B Hardener, Black | 11.6 lb (5.26 kg) Pail |

Theoretical Coverage 53.3 square feet per 2-gallon kit at 60 mils.
25.6 square feet per 2-gallon kit at 125 mils.

Coverage will vary depending on application. Allow for loss in mixing and application.

Storage & Shelf Life Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 24 months for part A and 12 months for part B when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C).

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

SAFETY

Safety Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

TYPICAL PHYSICAL PROPERTIES

| PROPERTY | VALUE |
|--|--|
| Pull-off adhesion, dry ASTM D4541 Blasted steel 1 coat | >2,850 psi (20 MPa) |
| Flash Point | Greater than 250°F (121°C) |
| Specific gravity | Part A: 0.53 Part B: 1.40 |
| VOC | 0 lb/gal (0 g/L) |
| Density | Part A: 12.7 lbs/gal (1.5 kg/L) Part B: 11.7 lbs/gal (1.4 kg/L) Mixed: 12.2 lbs/gal (1.5 kg/L) |

SERVICE TEMPERATURE

| SERVICE | MAXIMUM TEMPERATURE |
|--------------|---------------------|
| Dry | 350°F (176°C) |
| Splash/spill | 293°F (145°C) |
| Immersion | 194°F (90°C) |

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

Rev. 02/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.