

# CE-237 Page 1 of 2 Tufchem<sup>™</sup> Tiling Systems

**INSTALLATION GUIDANCE** 

### **SELECTION & SPECIFICATION DATA**

Туре	Chemical-resistant vitrified floor tiling system	Reference	CES-311 l	CES-311 Installation of Tufchem <sup>™</sup> Tiling Systems	
Description	Tufchem Tiling Systems are direct-bonded, pressure embedded and power grouted fully- vitrified tile flooring systems. The dense, impervious tiles feature integrally molded side joint spacers and a range of surface texture options to strike the right balance between walk work surface safety and ease of cleaning. Choose from traditional rectangular or modern hexagonal tiles available in an assortment of colors. Vibration setting compacts the epoxy Thinset <sup>™</sup> Adhesive or Thinset Novolac Adhesive	Specifications Installation Conditions CURE TIME	Tufchem Tiling Systems components are designed to be installed at temperatures between 50°F and 90°F (10°C and 32°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure.		
	bedding to maximize effective bearing area and	Installation Temp	erature	Initial Set	Full Cure
	tenaciously bond the tiles to the substrate. Power grouting with water cleanable Penntrowel™ EZ	70°F (21°C)		7 hours	5 days
	Grout 100 or 200 makes use of the built-in spacers and produces narrow side joints.			7 110015	5 days
Uses	Food processing plants	<u>SAFETY</u>			
0363	<ul> <li>Bakeries</li> <li>Breweries and distilleries</li> <li>Bottling plants</li> <li>Meat and poultry processing plants</li> <li>Pharmaceutical plants</li> <li>Chemical process facilities</li> </ul>	Safety	number o information on the inc	l applications of this f hazards. Read and on, precautions and dividual product lab fore using.	follow the hazard first aid directions
	Institutional kitchens	Ventilation		norough air circulati In until the material	
Features	<ul> <li>Self-spacing tiles enable high installation productivity</li> <li>Lower installed cost than conventional paver systems.</li> <li>Vibration setting minimizes tile lippage</li> <li>Hexagonal field tiling conforms tightly to changing slopes on floors with central drains</li> <li>Numerous solid and mingled color options create a uniquely attractive floor</li> <li>Choice of abrasion-resistant integrally molded surface textures to provide well-balanced slip resistance.</li> <li>Ease of cleaning for different processing environments.</li> <li>Antimicrobial by design. Consult ErgonArmor for details.</li> </ul>			nclosed areas.	
Limitations	<ul> <li>Not suitable for vertical wall tile applications.</li> <li>For hotter or more aggressive chemical service, set and grout the tiles using conventional methods using Furalac<sup>™</sup> Red Panel Grout, Pennchem<sup>™</sup> Tile Grout, or Pennchem<sup>™</sup> CIP Tile Grout to suit the exposure conditions.</li> </ul>				



## CE-237 Page 2 of 2 **Tufchem<sup>™</sup> Tiling Systems**

#### **PACKAGING & ESTIMATING**

Tufchem Tile are offered primarily in hexagonal and rectangular shapes.

Standard tile sizes are as follows: 4" x 8" x 3/4" (100 x 200 x 18 mm) 4-1/4" hexagonal x 3/4" (108 x 18 mm)

Membranes, leveling beds, tile adhesives and grout components are packaged as outlined on individual data sheets. Consult ErgonArmor for specific details.

#### Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life of components is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions. Tile pieces have an indefinite shelf life.

If there is any question with respect to the quality of the components check reactivity prior to use. For assistance consult with ErgonArmor.

### **TYPICAL PHYSICAL PROPERTIES**

Colors	Numerous solid and mingled colors		
Shape availability	Rectangular or hexagonal		
Slip resistance	Integrally molded profiles from flat to heavily textured		
Dimension tolerance , DIN 18-158	$<\pm0.5\%$ in length and width		
Thickness	3/4" (18-19 mm)		
Flexural strength	4,400 – 9,065 psi		
Water absorption	<0.25%		
Acid resistance, DIN EN99	No trace of deterioration		
Coefficient of thermal expansion	4-5 x 10 <sup>-6</sup> /cm/cm/°C at 100°C		
Hardness (Moh scale)	>7		
Nominal joint width	5/64" (3 mm) (integrally molded)		
Production method	Dry pressed		

Rev 07/2020

#### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.